




Grange Tubes

PTFE extruded products

Smooth Bore PTFE Convolute - SBC



ID Internal Diameter
 OD Outside Diameter
 MBR Minimum Bend Radius

Service Temp. Range	-70°C to +260°C
Shelf Life	N/A
Chemical Resistance	Virtually total
Water Absorption	0.01%
Flammability	Non-flammable UL94 Rating V-0
Dielectric Strength	19.7kV/mm
Tensile Strength	Longitudinal 33 N/mm ² Transverse 31 N/mm ²
Shore Hardness	D55
Colour Range	Natural.
Packaging	Random lengths on reel/coils. Please contact us for any special packaging requirements.
Value Added Services	Cut lengths; straightened, plugged or cuffed ends; flared ends; punched & drilled holes; slitting.

Part Code	ID		OD		MBR		Weight g/m	MOQ m
	in	mm	in	mm	in	mm		
SBC6.8	.270	6.8	.354	9.0	1.5	38	41	10
SBC7.9	.312	7.9	.394	10.0	1.5	38	56	10
SBC10	.394	10.0	.492	12.5	2	50	70	10
SBC13.6	.536	13.6	.640	16.2	3	76	110	5
SBC16.7	.658	16.7	.787	20.0	4	100	161	4
SBC19.8	.780	19.8	.913	23.2	5	126	179	3
SBC25.4	1.023	26.0	1.193	30.3	6	150	268	3

