


Grange Tubes

PTFE extruded products

Imperial PTFE Rod



Service Temp. Range	-70°C to +260°C
Shelf Life	N/A
Chemical Resistance	Virtually total
Water Absorption	0.01%
Flammability	Non-flammable UL94 Rating V-0
Dielectric Strength	19.7kV/mm
Tensile Strength	Longitudinal 33 N/mm ² Transverse 31 N/mm ²
Shore Hardness	D55
Colour Range	12 colours including natural
Packaging	Reels or coils.
Applicable Standards	BS 6564; BS EN ISO 13000
Value Added Services	Cut lengths; cut pieces.

Part Code	OD		MOQ
	Inches	mm	
1/32	0.031 ± .005	0.79 ± 0.13	3000
1/16	0.063 ± .005	1.59 ± 0.13	800
3/32	0.093 ± .005	2.36 ± 0.13	350
1/8	0.125 ± .005	3.18 ± 0.13	200
5/32	0.156 ± .005	3.97 ± 0.13	100
3/16	0.187 ± .005	4.75 ± 0.13	100
1/4	0.250 ± .008	6.35 ± 0.20	50
5/16	0.313 ± .008	7.94 ± 0.20	30
3/8	0.375 ± .010	9.53 ± 0.25	20

