



Grange Tubes

PTFE extruded products

Technical Information

General Properties of P.T.F.E. (Polytetrafluoroethylene) (CF₂)ⁿ

IMPORTANT NOTE: This data is intended as a guide and is taken from polymer manufacturers' data. Grange Tubes LLP cannot take responsibility for the accuracy of the data, and customers must evaluate the material under the relevant conditions if the properties are critical to their applications.

Temperature Resistance	PTFE is extremely stable at high temperatures, and can be used continuously at 260°C. Although it is stable at high temperatures, its mechanical properties decrease with increasing temperature.			
	-70°C to +260°C			
Chemical Resistance	PTFE is one of the few polymers that retain a measure of toughness and strength even at cryogenic temperatures. It has been used safely in outer space at temperatures approaching absolute zero.			
	PTFE is virtually inert to all chemicals. It is resistant to fuming sulphuric and nitric acids, aggressive peroxides, amines, antioxidants (as used in high temperature oils), and methanol (as used in fuel). The only materials known to react with PTFE are: Elemental alkali metals (molten or in solution); Finely divided metal powders (only when ignited); Finely divided mixtures of bronze powder and molybdenum disulphide; Fluorine; Chlorine trifluoride; 80% NaOH or KOH solutions (above 300°C). It is resistant to fuming sulphuric and nitric acids, aggressive peroxides, amines, antioxidants (as used in high temperature oils), and methanol (as used in fuel).			
Solvent Resistance	Organic solvents do not attack or dissolve PTFE, although some permeation may occur as a result of both absorption and diffusion. Obviously, the void content of a finished part will affect permeability significantly.			
	PTFE contains no extractables which can leach out and interact unfavourably with adjacent materials.			
Weathering	PTFE is extremely hydrophobic, and sheds water almost totally. PTFE is also virtually unaffected by oxygen, ozone and visible or UV light. It shows no ageing since no plasticisers, antioxidants or other additives are used during its processing.			
Water Absorption	Max 0.01%			
Flammability	PTFE is essentially non-flammable. It will sustain combustion only in an environment containing >95% oxygen. The flash point is 530°C. It has a UL 94 rating V-0. PTFE does not drip when heated over its gel transition point. This provides an additional safety margin in case of fire.			
Friction & Anti-Stick Properties	PTFE has an extremely low coefficient of friction. The lowest values are obtained under conditions of high pressure and low velocity. Unfilled PTFE wears relatively fast, and is unfit for dynamic bearing applications. Due to its very low surface energy PTFE has excellent anti-stick properties, preventing the build up of sediment or carbon.			
Electrical Properties	PTFE has unique electrical properties; a very low dielectric constant and dissipation factor, excellent dielectric strength, and a very high volume and surface resistivity.			
	Dielectric Strength	19.7 kV/mm	ASTM D149	
	Volume Resistivity	10 ¹⁸ Ωcm	ASTM D257	
Mechanical Properties	Tensile Strength	Longitudinal	33 N/mm ²	DIN 53455
		Transverse	31 N/mm ²	ASTM D1457-81
	Elongation at Break	Longitudinal	350%	DIN 53455
		Transverse	610%	ASTM D1457-81
	Density		2.15 g/cm ³	ASTM D1457-81
	Shrinkage	Longitudinal	11%	
		Transverse	15%	
	Shore Hardness		D 55	ASTM D2240
Thermal Properties	Service Temperature Range		-70 °C to +260°C	
	Gel Transition Range		320 °C to 340°C	DTA
	Thermal Conductivity		0.25 - 0.50W/m.K	DIN 52612
Shelf Life & Storage:	No special requirements*			
	*PTFE Heat Shrink conforming to AMS-DTL-23053/12 specifies a shelf life of 4 years when stored at +18 to +35°C			

DISCLAIMER: The information in this Data Sheet is believed to be correct as of the date issued, no warranty is given as to the fitness of the Product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that such exclusion is permitted by law. User is responsible for determining whether the product is fit for a particular purpose and suitable for user's method of use or application. Given the variety of factors that can affect the use and application of a product, some of which are uniquely within the user's control, it is essential that the user evaluate the product to determine whether it is fit for a particular purpose and suitable for user's method of use or application. The information is subject to change without notice and replaces all data sheets previously supplied. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where Grange Tubes LLP was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict Grange Tubes LLP's liability for death or personal injury resulting from its negligence.

